


STYLE: AF-5400

Proved suitable for extreme application range, AF-5400 is widely used in process piping and equipment in chemical, pulp and paper and many other industrial applications. High quality non-asbestos fiber (Aramid Fiber) and excellent heat/oil resistant Nitrile Rubber (NBR) are compounded and calendared into a gasket sheet well suited for use with steam hot oil, oil gas, etc



TYPICAL PROPERTIES

Color	Golden, Branded
Fiber:	Aramid
Binder:	Nitrile (NBR)
Fluid Service:	Steam, Water, Oils, Dilute Acids & Alkalies, Hydrocarbons, Solvents, Refrigerants.
Density:	1.7 g/cm³
Tensile Strength ASTM F 152:	1800 psi (12.4Mpa)
Change in Tensile, ASTM F-152	30% Max
Compressibility ASTM F 36:	8 to 16%
Recovery ASTM F 36:	50%
Temperature	
Range:	-100 to 800°F (-73 to 427°C)
Max. Continuous :	554°F (290°C)
Max. Pressure:	1500 psig (103 bar)
Fluid Resistance-ASTM F146	
IRM 903 Oil, 5h/300°F (150°C)	
Thickness increase:	0 to 15%
Weight increase:	15%
ASTM Fuel B 5h/70°F (21°C)	
Thickness Increase:	0 to 10%
Weight increase:	15%
Sealability	
ASTM F 37 (Fuel A):	0.03ml/hr
ASTM F37 (Nitrogen):	0.5 ml/hr
Dielectric Breakdown ASTM D 149:	14kV/mm (370V/mil)
DIN 3535 Gas Permeability:	0.05cc/min
Creep relaxation ASTM F 38:	25%
Flexibility ASTM F1 47:	8x

Gasket Factors of Araflex-FLEXGUARD 300	1/16"		1/8"
THICKNESS	3.7	3.0	
m factor	3515 (24.2)		4010 (27.50)
y psi (Mpa)			

Note: ASTM properties based on 1/16" sheet thickness except ASTM F38, which is based on 1/32" sheet thickness. This is a general guide only and should not be the sole means of accepting or rejecting this material. The data listed here falls within the normal range of product properties but should not be used to establish specification limits nor used alone as the basis of design.

AraflexWarning: Araflex gasket materials should never be recommended when both the temperature and the pressure are at the maximums listed. Properties and applications shown are typical. No application should be undertaken by anyone without independent study and evaluation for suitability. Never use more than one gasket in one flange joint, and never reuse a gasket. Improper use or gasket selection could cause property damage and/or serious personal injury. The data reported is a compilation of field testing, field service reports and/or in-house testing. While the utmost care has gone into publishing the information contained herein, we assume no responsibility for errors. The information and specifications contained in this website are subject to change without notice. This revision cancels and obsoletes all previous editions.